

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

A1. 1. (Amended) A textile fabric comprising: a woven material of spun yarns including first staple being a polymer selected from the group consisting of PBI, PBO, or melamine formaldehyde, and a second staple of an aramid polymer; and multi-filament yarns including an aramid filament, wherein the weight ratio of said spun yarn to said multi-filament yarn ranges from 85:15 to 92:8.

2. (Cancelled) ✓

A2. ~~2.~~ (Amended) The fabric of claim [2] 1 wherein the weight ratio is 90:10.

A2. 3/4. (Original) The fabric of claim 1 wherein the woven fabric weight ranging from 6 to 8 OSY.

5. (Original) The fabric of claim 1 wherein the woven fabric has a weave selected from the group consisting plain, twill, rip stop, or oxford.

6. (Original) The fabric of claim 1 wherein the spun yarn ranges from 32/2 to 16/2 c.c.

7. (Original) The fabric of claim 1 wherein the multi-filament yarn ranges from 200 to 1500 denierThe fabric of claim 1 wherein the multi-filament yarn ranges from 200 to 1500 denier.

8. (Original) The fabric of claim 1 wherein the multi-filament yarn being inserted among the spun yarn at a ratio of 1:5 to 1:20.

9. (Original) A textile fabric comprising: a woven material of spun yarn, said spun yarn being a blend of staple, a first staple being made of a polymer selected from the group consisting of PBI, PBO, melamine formaldehyde, or combinations thereof and a second staple being made of an aramid, and a multi-filament yarn including aramid filaments, said multi-filament yarns being inserted into said woven material, in both the warp and the weft, at a multi-filament yarn to spun yarn ratio of 1:5 to 1:20.

10. (Original) The fabric of claim 9 wherein said spun yarn being a blend of PBI and aramid staple.

11. (Original) The fabric of claim 9 wherein said spun yarn being a blend of PBO and aramid staple.

12. (Original) The fabric of claim 9 wherein said spun yarn being a blend of PBI, PBO, and aramid staple.

13. (Original) The fabric of claim 9 wherein the spun yarn ranges from 32/2 to 16/2 c.c.

14. (Original) The fabric of claim 9 wherein the multi-filament yarn ranges from 200 to 1500 denier.

15. (Original) The fabric of claim 9 wherein the woven fabric weight ranging from 6 to 8 OSY.

16. (Original) The fabric of claim 15 wherein the woven fabric has a weave selected from the group consisting plain, twill, rip stop, or oxford.